

KEY RESIN COMPANY

KEY LASTIC ME

DESCRIPTION

KEY LASTIC ME is a fluid applied, resilient flooring system specially formulated for concrete floors in mechanical equipment rooms. The resiliency of **KEY LASTIC ME** provides sound-deadening qualities and cushioning under foot.

KEY LASTIC ME exhibits excellent adhesion and abrasion, impact, and chemical resistance. Its elastomeric properties will allow for horizontal movement of up to 1/8" without fracturing **KEY LASTIC ME**.

The surface characteristics of **KEY LASTIC ME** can be varied to accommodate the degree of skid resistance, the decorative appearance, and the chemical resistance.

KEY ADVANTAGES

- High Wear and Abrasion Resistance
- Low Maintenance
- Safe (non-skid)
- 100% Solids Provides Low Odor Application
- Chemical Resistant Finishes are Available

KEY CONSIDERATIONS

- On or below grade installation must have an efficient vapor barrier under the slab.
- Special treatments are necessary where hydrostatic pressure or moisture vapor transmission may be present.
- Substrate temperature must be a minimum of 55°F (Low temperature cure system available on request).
- Substrate must be free of dirt, waxes, curing agents, and other foreign materials.
- All control joints and expansion joints in the substrate must be revealed with the appropriate divider strips in the topping.

TYPICAL USES

KEY LASTIC ME is a 1/8" system ideal for use in mechanical equipment rooms, machine shops, or other light production areas.

SELECTION GUIDE

↑	Activity Centers
	Aircraft Hangars
	Airports
	Baggage/Service Terminals
↑	Animal Areas
↔	Housing
	Cage Washing
	Beverage
	Processing
	Packaging/Warehousing
	Bottling
↔	Cafeterias
	Chemical Processing
↑	Clean Rooms
↔	Coolers
	Computer Assembly
	Commercial Kitchens
↑	Containment Areas
	Convention Centers
↑	Correctional Facilities
↑	Corridors
	Docks/Ramps
↔	Dairies
	Distilleries
	Packaging
	Bottling
	Food
	Processing
	Preparation Service
↔	Garages
	Hospitals
	Corridors & Lobbies
	Patient Rooms
	Operating Rooms
	Services
↔	Laboratories
↔	Laundries
↑	Locker Rooms
↑	Machine Shops
↑	Manufacturing
	Light Duty
	Heavy Duty
	Meat, Fish, Poultry Processing
↑	Mechanical Equipment Rooms
	Munitions Facilities
↔	Parking Garages
	Interior Decks
	Exterior Decks
↔	Pharmaceutical Plants
	Pulp and Paper Processing Facilities
↑	Schools
	Shopping Malls
↑	Showers
	Utilities
↑	Warehouses
	Waste Water Treatment Facilities

↑-Excellent Choice ↔-Alternate Choice

TECHNICAL DATA

System Performance Properties

Flammability ASTM D-635	Self Extinguishing
Fungus & Bacteria Growth MIL-F-52505 §4.4.2.11	Will not support growth of fungus or bacteria when subjected to mildew and bacteria tests.
Hardness ASTM D-2240	50 Shore D
Bond Strength to Concrete ACI COMM #403, Bulletin 59-43	300 psi (100% concrete failure)
Resistance to Elevated Temperature MIL-D-3134F §4.7.4	No slip or flow at required temperature of 158°F
Coefficient of Friction ASTM D-2047	0.60
Water Absorption ASTM D-570	Nil
Thermal Shock Resistance ASTM C-884	Passes
Abrasion Resistance ASTM D-4060	Will vary with finish
Impact Resistance MIL-D-3134F §4.7.3	Withstands 16 ft./lbs. without cracking, delamination, or chipping.
Compressive Strength ASTM C-579, 7 days	5,000 psi
Tensile Strength ASTM C-307	1,200 - 1,500 psi
Thermal Coefficient of Expansion ASTM C-531	12-15 x 10 ⁻⁶

APPLICATION

Concrete surfaces must be in sound condition and properly prepared prior to any **KEY RESIN COMPANY** flooring system installation. Refer to **Key Resin Company Technical Bulletin #1** for specific preparation guidelines.

Installation of **KEY LASTIC ME** involves several steps including priming, applying successive base coats, broadcasting quartz aggregates, grouting, and sealing. For specific installation guidelines consult **Key Resin Company's Installation Instruction Manual**.

MAINTENANCE

After completing the application of **KEY LASTIC ME**, the installer should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly.

KEY LASTIC ME is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Waxing is optional. Long periods of heavy traffic may cause wear patterns necessitating a maintenance application of a finish coat.

WARRANTY Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Membrane Performance Properties

Ultimate Tensile Strength ASTM D-638	1,000-1,200 psi
Tensile Elongation ASTM D-638	100%
Hardness ASTM D-2240	80 Shore A

COMPOSITION

100% solids flexible epoxy base coats broadcast with quartz aggregates. Urethane and epoxy finish coats provide specific performance characteristics.


COLOR & AVAILABILITY

KEY LASTIC ME is available in a variety of standard colors. Custom colors are available subject to laboratory approvals, minimum quantities, lead time for production and increased cost. Colors will not fade or wear thin.

Key Flooring Systems are available throughout the United States, Canada, and a number of other countries. Contact the **KEY REPRESENTATIVE** in your area for details.


TECHNICAL SERVICE

Key Resin Company and KRC Associates, Inc. provide services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **KEY REPRESENTATIVES** are available to assist you at any time. CALL (888)943-4532.



KEY RESIN COMPANY

4061 Clough Woods Drive
Batavia, Ohio 45103, 888.943.4532



Key Lastic ME-2