



DIAMOND 450 No VOC* Interior Semi-Gloss Paint 7400-XXXXN

DESCRIPTION

GLIDDEN PROFESSIONAL™ Diamond 450 No VOC* is our finest interior product, providing a high performance finish that is 10X tougher than traditional finishes. The premium ingredients in this 100% acrylic formula provide a durable coating that lasts longer, is scrub and burnish resistant, and is tintable into the LUMITEC

TECHNOLOGY® color range, for brighter, cleaner colors. This anti-microbial coating also contains agents that inhibit mold & mildew growth in the paint film.

* CONTAINS NO VOCs - VOC (Volatile Organic Compounds) content as measured by the Environmental Protection Agency (EPA) Reference Test Method 24

CERTIFICATIONS

| AS OF 7/1/2009, COMPLIES WITH | |
|-------------------------------|----------|
| MPI# | 141, 147 |
| LEED | Yes |
| CHPS | Yes |
| GREENGUARD | No |
| AIM | Yes |
| OTC/LADCO | Yes |
| CARB | Yes |
| SCAQMD | Yes |

PERFORMANCE DATA

| CHARACTERISTIC: | RESULTS: |
|---|-------------------------------|
| Dry Hide* | ★★★★★★★★☆☆ |
| Adhesion* | ★★★★★★★★☆☆ |
| Moisture Resistance* | ★★★★★★★★☆☆ |
| Block Resistance* | ★★★★★★★★☆☆ |
| Shim Scrub Resistance* | ★★★★★★★★☆☆ |
| Washability* | ★★★★★★★★☆☆ |
| Sag Resistance | 14-18 mils wet |
| Air and Substrate Application Temperature | 50° F (10° C) - 90° F (32° C) |
| Service Temperature Limits | 200° F (93° C) |
| Storage Temperature | 40° (4° C) F - 95° F (35° C) |

*Performance ratings are based on product comparisons to other products in that sheen range, performed at 77° F (25° C) 50% RH. Rating scale is from 1-10, 10 being the highest rating.

COMPOSITION

- 100% Acrylic Resin
- Titanium Dioxide and Extender Pigments
- Not manufactured with lead or mercury containing materials.

SPECIFICATION

Color:

White & custom colors

Clean-up Solvent:

Soap and water

Finish: Semi-Gloss

Sheen: 65 - 75 units maximum @ 85°

Gloss: 35 - 55 units maximum @ 60°

Density:

10.36 lbs/gal (1.24 kg/L)

Solids:

Volume - 41% +/- 1%

Weight - 51% +/- 1%

VOC:

0.0 lbs/gal (0.0 g/L) maximum
per EPA Reference Test Method 24

Refer to MSDS for regulatory VOC
content of complete product line.

Theoretical Coverage @ 1 mil dry:

660 sq ft/gal (16 m²/L)

Practical Coverage:

Apply at 450-500 sq ft/gal (11-12 m²/L).
Actual coverage may vary depending on
substrate and application method.

Recommended Film Thickness:

3.2 - 3.6 mils wet

1.3 - 1.5 mils dry

Airless Spray Application:

Pressure - 2000 psi

Tip - .015" - .019"

Dry Time 77°F (25°C) & 50% RH:

To touch - 30-60 minutes

To recoat - 2-4 hours

Flame Spread Rating:

Class A (0-25) on non-combustible
surfaces

Flash Point:

None

Shelf Life:

1 year minimum - unopened



www.gliddenprofessional.com

9 FINISHES
PAINTING (00900)



SURFACE PREPARATION

GENERAL SURFACE PREPARATION:

All surfaces must be sound, dry, clean and free of oil, grease, dirt, rust, mildew, form release agents, curing compounds, loose and flaking paint and other foreign substances.

NEW SURFACES:

Drywall:

- Joint compound must dry for two days before priming
- Dust Clean
- For lowest odor system, prime with 9116 LIFEMASTER® No VOC* Interior Primer Sealer
- 1000 High-Hide Primer Sealer may also be used

Wood:

- Set nails, fill with latex spackle
- Sand smooth
- Dust clean
- For lowest odor system, prime with 9116 LIFEMASTER No VOC* Interior Primer Sealer
- 3210 GRIPPER® Interior Exterior Primer Sealer or 1010 STAIN JAMMER® Latex Primer Sealer may also be used

Concrete, Plaster and Masonry:

- Cure at least 30 days before painting
- pH must be 10.0 or lower
- Roughen slick poured or precast concrete and remove sealers by chemical cleaning or abrasive method such as sandsweeping
- Rinse thoroughly with water and allow to dry
- Must be internally dry
- Remove loose aggregate
- Prime concrete and plaster with 9116 LIFEMASTER No VOC* Interior Primer Sealer or 3210 GRIPPER Interior Exterior Primer Sealer
- Product may be used as self-priming on concrete, used as a primer under itself
- Fill concrete block with 3010 Concrete Coatings Block Filler

Steel:

- Performance over hand or power tool cleaned surfaces is dependent on the degree of cleaning
- Prime with Devflex 4020PF Direct-to-Metal Primer or DEVGUARD® 4360 Low VOC Universal Primer

Galvanized Metal and Aluminum:

- Clean off oils and other contaminants
- Prime with 3210 GRIPPER Interior Exterior Primer Sealer, Devflex 4020PF Direct-to-Metal Primer or DEVGUARD 4360 Low VOC Universal Primer

PREVIOUSLY PAINTED SURFACES:

- Wash to remove contaminants
- Rinse thoroughly with water and allow to dry
- Dull glossy areas by light sanding
- Remove sanding dust
- Remove loose paint
- Prime bare areas with primer specified under **NEW SURFACES**

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear an NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

DIRECTIONS FOR USE

TINTING:

Tint the appropriate base with DRAMATONE™ colorants.

SPREADING RATE:

Apply at 450-500 sq ft/gal (11-12 m²/L). Actual coverage may vary depending on surface texture, porosity and application method. For best hiding of bright or accent colors, prime with the appropriate grey base. Certain shades of yellow, orange, pink and red may require multiple coats.

APPLICATION:

Mix thoroughly before use. May be applied by brush, roller or airless spray. No thinning required. For airless spray, use a .015"-.019" tip at 2000 psi, adjust pressure as needed. Do not apply when the surface or air temperature is below 50F (10C). Provide good ventilation and warmth for normal drying.

DRYING TIME:

At 77F (25C) and 50% R.H., dries to touch in 30 to 60 minutes and to recoat in two to four hours. Low temperature, high humidity, thick films or poor ventilation will increase these times.

CLEAN-UP:

Clean hands and tools immediately with warm, soapy water. Clean spills right away with a damp cloth.

WASHING INSTRUCTIONS:

After 30 days or when paint has fully cured, areas may be washed using a non-abrasive, mild detergent solution and cellulose sponge.

PRECAUTIONS

WARNING! CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. MAY BE HARMFUL IF SWALLOWED. WHEN TINTED, CONTAINS ETHYLENE GLYCOL WHICH CAN CAUSE SEVERE KIDNEY DAMAGE WHEN INGESTED AND HAS BEEN SHOWN TO CAUSE BIRTH DEFECTS IN LABORATORY ANIMALS. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. For emergency information call (800) 545-2643. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information.** If sanding, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. Avoid contact with eyes and skin. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** For skin contact, wash thoroughly with soap and water. If any product remains, gently rub with petroleum jelly, vegetable or mineral/baby oil then wash again with soap and water. Repeat as needed. Remove contaminated clothing. For eye contact, flush immediately with plenty of water for at least 15 minutes. **Get medical attention.** If swallowed, **get medical attention immediately.** If inhalation causes discomfort, remove to fresh air. If discomfort persists or breathing difficulty occurs, get medical attention. **KEEP FROM FREEZING.** DS10-1005

SHIPPING

FREIGHT CLASSIFICATION:

Paint, Freezable

PACKAGING:

1 gallon (3.785 L)
5 gallons (18.925 L)

FLASH POINT:

None



Akzo Nobel Paints LLC, Strongsville, Ohio 44136



www.gliddenprofessional.com

LIMITATION OF LIABILITY To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.