



LATAPOXY® 300 Adhesive

DS-633.0-1107



1. PRODUCT NAME

LATAPOXY® 300 Adhesive

2. MANUFACTURER

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Telephone: 203.393.0010, ext. 235
Toll Free: 800.243.4788, ext. 235
Fax: 203.393.1684
Internet: www.laticrete.com

3. PRODUCT DESCRIPTION

LATAPOXY 300 Adhesive is a chemical resistant, epoxy adhesive that will bond to most sound, clean surfaces. Adhesive spreads easily and cleans with water while fresh. LATAPOXY 300 Adhesive is a factory-proportioned kit consisting of epoxy resin, hardener and chemical resistant silica filler. LATAPOXY 300 Adhesive can be used in interior and exterior (see limitations) walls and floors, wet and dry areas.

Uses

For heavy duty commercial chemical resistant installations in food processing areas, commercial kitchens, restaurants, etc. Also use LATAPOXY 300 Adhesive to install all types of ceramic tile, marble and natural stone over post-tensioned and precast floor systems. Also recommended for rubber flooring and wood block floors and the installation of green marble, white marble and agglomerate marbles that have a tendency to stain, darken or warp when installed with water-based installation materials.

Note: The Tile Council of North America recommends the use of epoxy adhesives and grouts for thin-set installations on suspended concrete slabs and for floors and walls when chemical resistance is required.

Advantages

- Water cleanable.
- No flammable solvents are required to clean tools or finished work.
- Ideal for installing moisture sensitive marble and agglomerate tiles.
- Ideal for the installation of resin backed tile, mosaics, stone, and agglomerates.
- Non-staining on white and light-colored marble.
- High bond strength.
- Maximum chemical resistance.

Suitable Substrates

- Concrete
- Ceramic tile and stones
- Exterior glue plywood*
- Concrete masonry
- Brick masonry
- Non-water soluble cut-back adhesive
- Vinyl or other resilient tile*
- Cement mortar beds
- Gypsum wallboard*
- Cement plaster
- Cement terrazzo
- Plastic laminate*
- Cement backer board**
- Steel

* Interior application only.

** Consult cement backer board manufacturer for specific installation recommendations and to verify acceptability for exterior use.

Packaging

LATAPOXY 300 Adhesive is a factory proportioned kit with resin, hardener and filler powder, packed in a plastic mixing pail together with rubber gloves, cleaning pad and instructions.

Unit Sizes

#2 Unit

Weight: 25.2 lb (11.4 kg) volume: 1.8 gals (6.8 l)

Approximate Coverage

	#2 Unit
With 1/16" (1.5 mm)* v-notch trowel	180-200 sq. ft / 16.2-18 m ²
With 3/16" (4 mm) v-notch trowel	70-80 sq. ft / 6.3-7.2 m ²
With 1/8" x 1/8" (3 x 3 mm) square notch trowel	90-110 sq. ft / 8.4-102 m ²
With 1/4" x 1/4" (6 x 6 mm) square notch trowel	30-35 sq. ft / 2.8-3.3 m ²

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years*.

* High humidity will reduce the shelf life of bagged product.

Limitations

- Not for use as a grout. Use LATICRETE® SpectraLOCK® † PRO Grout; LATAPOXY® SP-100 or LATAPOXY 2000 Industrial Grout.
- † United States Invention Patent No.: 6881768 (and other Patents)
- Do not install when surface temperature is below 60°F (16°C) or above 90°F (32°C).
- Adhesives for ceramic tile and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE Waterproofing Membrane (see Section 10 **FILING SYSTEMS**).
- Consult LATICRETE Technical Services on limitations for exterior installations.
- When installing ceramic tile and stone, verify that substrate deflection does not exceed the maximum allowable industry standard of L/360 for ceramic tile and L/480 for stone under combined live and dead loads. Some marbles and other stone have low flexural strength and may not be suitable for installation over wood floors.

Cautions

Consult MSDS for more safety information.

- During cold weather, protect finished work from traffic until fully cured.
- LATAPOXY 300 Adhesive Part A is corrosive until fully cured. Damage to eyes or skin is possible.
- Contains silica sand. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- Keep out of reach of children.

4. TECHNICAL DATA

VOC/LEED Product Information



This product has been GREENGUARD Indoor Air Quality Certified® by the GREENGUARD Environmental Institute under the GREENGUARD Standard for Low Emitting Products in finished form.

Total VOC Content pounds/gallon (grams/liter) of product in unused form is 0.0067 lb/gal (0.80 g/l).

Applicable Standards

ANSI A118.3, EN 12004

Performance Properties



Test	Method	Results	Specification
Quarry Tile Shear Bond Strength	ANSI A118.3-5.5	>1250 psi (8.6 MPa)	>1000 psi (6.9 MPa)
Tensile Strength	ANSI A118.3-5.7	1400-1700 psi (9.6-11.7 MPa)	>1000 psi (6.9 MPa)
Compressive Strength	ANSI A118.3-5.6	5000-5400 psi (34.4-37.2 MPa)	>3500 psi (24.1 MPa)
Thermal Shock Resistance	ANSI A118.3-5.8	600-700 psi (4.1-4.8 MPa)	>500 psi (3.4 MPa)
Shrinkage	ANSI A118.3-5.3	0-0.1%	<0.25%
Sag Resistance	ANSI A118.3-5.4	Pass	No shape change
Water Cleanability	ANSI A118.3-5.1	>80 minutes	>80 minutes

Initial Shear Adhesion	EN12003 7.3	≥2 N/mm ²	≥2 N/mm ²
Shear Adhesion Strength after Water Immersion	EN12003 7.4	≥2 N/mm ²	≥2 N/mm ²
Shear Adhesion After Thermal Shock	EN12003 7.5	≥2 N/mm ²	≥2 N/mm ²
Open Time Tensile Adhesion Strength	EN1346	>0.5 N/mm ² in not less than 20 minutes	>0.5 N/mm ² in not less than 20 minutes

Data from TCA054-05, TCA 095-90, and 50/0776/05.

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

Classification in Compliance with EN 12004

LATAPOXY 300 Epoxy Adhesive is an improved reaction resin adhesive classified as R2.

LATAPOXY 300 Epoxy Adhesive is CE marked, as declared in report no. 50/0776/05 issued by Materialprüfungs- und Versuchsanstalt Neuwied Forschungsinstitut für Vulkanische Baustoffe GmbH (Neuwied, Germany)

Working Properties (70°F [21°C])

Pot Life	45 minutes
Time to Grout	12 hours
Time to Light Traffic	12 hours
Time to Heavy Traffic	24 hours
Minimum Application Layer	1/8 in (3 mm)
Maximum Application Layer	3/8 in (9 mm)
Wet Density	99 lbs/ft ³ (1590 kg/m ³)

CHEMICAL RESISTANCE CHART

LATAPOXY 300 Adhesive

REAGENT TYPE at (70°F [21°C])	LATAPOXY® 300 Adhesive EXPOSURE LEVEL	
	Intermittent	Constant
Citric Acid 10%	R	R
Sulfuric Acid 10%	R	R
Hydrochloric Acid 10%	R	R
Lactic Acid 5%	R	R
Vinegar	R	NR
Acetic Acid 10%	R	NR
Nitric Acid 10%	R	R
Sodium Hydroxide 10%	R	R
Sodium Chloride 10%	R	R
Concentrated Detergents	R	R
Ammonium Hydroxide	R	R
Sugars	R	R
Gasoline	R	R
Cooking Oils	R	R
Turpentine	R	R
Mineral Spirits	R	R
Toluene	NR	NR
Xylol	NR	NR

R= Recommended NR= Not Recommended

Chemical Resistance determined in accordance with ASTM C267-1982.

NOTES TO SPECIFIER: Use the constant exposure recommendations for intermittent exposure to reagents at temperatures above 90°F (32°C).

5. INSTALLATION

Surface Preparation

All surfaces should be between 60°F (16°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with LATICRETE Latex Portland Cement Underlayment to provide a wood float (or better) finish. Installation may be made on a damp surface. New concrete slabs must be damp cured and 28 days old prior to application. All slabs must be plumb and true to within 1/4" (6 mm) in 10 ft (3 m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 "Requirements for

Movement Joints: Preparations by Other Trades” or TCNA detail EJ-171 “Movement Joints—Vertical & Horizontal”. Do not cover expansion joints with mortar.

Note: Temperature will effect working properties of LATAPOXY 300 Adhesive. Warm temperatures will speed curing and shorten working time. Cool temperatures will slow curing and require longer time to traffic. Store LATAPOXY® 300 Adhesive at 70°F (21°C) for 24 hours prior to use.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.
2. Minimum construction for interior plywood floors.

SUBFLOOR: 5/8" (15 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported by a framing member; glue sheets to joints with construction adhesive.

UNDERLAYMENT: 5/8" (15 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 “Bonding Ceramic Tile Stone or Brick Over Wood Floors” for complete details.

3. **DO NOT** bond to particle board, luan, Masonite® or hardwood surfaces.

Mixing

Pour LATAPOXY 300 Adhesive Part A and Part B into a clean mixing pail and mix thoroughly. Add LATAPOXY 300 Part C Filler Powder and mix to a smooth, trowelable consistency. Mortar is ready for use immediately after mixing.

Application

Apply mortar to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side.

Note: Use the proper sized notched trowel to ensure full bedding of the tile. Back butter large tiles > 8" x 8" (>200 mm x 200 mm) to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet



to embed tile and adjust level. Check mortar for complete coverage by periodically removing a tile and inspecting bedding mortar transfer onto back of tile.

6. AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY materials are available worldwide. For Distributor information, call:

Toll Free: 800.243.4788

Telephone: 203.393.0010

For on-line Distributor information, visit LATICRETE at www.laticrete.com.

Cost

Contact a LATICRETE Distributor in your area.

7. WARRANTY

See 10. Filing System

DS 230.13: LATICRETE Product Warranty

A component of:

DS 230.12: LATICRETE 10 Year System Warranty

DS 230.14: LATICRETE 15 Year Residential Warranty

DS 700.12: LATICRETE Lifetime Residential Warranty

8. MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. TECHNICAL SERVICES

Technical assistance

Information is available by calling the LATICRETE Technical Service Hotline (hours 8:00 AM to 5:30 PM EST):

Toll Free: 800.243.4788, ext. 235

Telephone: 203.393.0010, ext. 235

Fax: 203.393.1948

Technical and safety literature

To acquire technical and safety literature, please visit our website at www.laticrete.com.

10. FILING SYSTEM

Additional product information is available on our website at www.laticrete.com. The following is a list of related documents:

DS 230.13: LATICRETE Product Warranty

DS 230.12: LATICRETE 10 Year System Warranty

DS 230.14: LATICRETE 15 Year Residential Warranty

DS 700.12: LATICRETE Lifetime Residential Warranty

DS 631.0: LATAPOXY SP-100

DS 236.0: LATICRETE 9235 Waterproofing Membrane

DS 685.0: LATICRETE SpectraLOCK® PRO Grout

† United States Invention Patent No.: 6881768 (and other Patents)

DS 634.0: LATAPOXY 2000 Industrial Grout

LATICRETE International, Inc.
One LATICRETE Park North
Bethany, CT 06524-3423 USA
1.800.243.4788
+1.203.393.0010
www.laticrete.com

©2008 LATICRETE International, Inc.
LATICRETE, LATAPOXY, SPECTRALOCK and the  logo are Registered Trademarks of LATICRETE International, Inc.

GREENGUARD Indoor Air Quality Certified is a Registered Trademark of the GREENGUARD Environmental Institute.

DS-633.0-1107