



Smart Ideas. Better Insulation.

FSK-25 Faced Batts

Flame-resistant Formaldehyde-free
Thermal and Acoustical Fiber Glass Insulation



FORMALDEHYDE-FREE

Johns Manville has revolutionized the building insulation industry by introducing an entire line of formaldehyde-free fiber glass building insulation. JM Formaldehyde-free insulation provides the same high-quality thermal and acoustical properties as conventional JM fiber glass – just without the formaldehyde-based binder. Why? Because it's a smart thing to do for our customers and the environment. Formaldehyde has traditionally been used as part of the binder in fiber glass insulation. Although there is no health risk with the traditional product, formaldehyde at higher levels may cause irritation and sensitivity. JM Formaldehyde-free building insulation utilizes an innovative new acrylic binder that eliminates binder-related formaldehyde emissions during manufacturing and, once installed, will not off-gas formaldehyde in the indoor environment. No formaldehyde means fewer things to worry about. Visit us at www.jm.com for more information.

PRODUCT DESCRIPTION

Johns Manville FSK-25 faced insulation is a lightweight flame-resistant thermal and acoustical fiber glass insulation made of long, resilient glass fibers bonded with an acrylic thermosetting binder. The batts are laminated with an FSK (foil-scrim-kraft) facing, which enables the insulation to carry a fire hazard classification rating of 25/50 or less per ASTM E 84 and also serves as an excellent vapor retarder. FSK-25 may be left exposed where codes permit.

APPLICATIONS

New Construction

- Wood frame construction – residential homes and light commercial buildings
- Metal frame construction – commercial buildings

Retrofit

- Masonry walls
- Under roof decks

INSTALLATION

FSK-25 faced insulation cuts easily with an ordinary utility knife. Stapling tabs are provided for attachment to wood framing. The insulation can also be installed with fasteners or simply pressed in place between studs or joists/rafters. FSK-25 faced insulation must be protected from outside elements like wind, rain and sunlight.

Note: In colder climate areas, vapor retarders (whether attached to the insulation or applied separately) are often placed toward the heated or conditioned side of the wall. This is done to reduce water vapor penetration into the wall from the building interior. Conversely, in predominantly hot, humid climates local practices often call for placing the vapor retarder toward the outside of the wall cavity. Check your local building codes for vapor retarder requirements.

PACKAGING

FSK-25 faced insulation is compression-packaged for savings in storage and freight costs.

RECOMMENDED STORAGE AND TRANSPORT

Store insulation indoors. Keep insulation clean and dry at all times. When transporting, cover completely with a waterproof tarpaulin as necessary.

SPECIFICATION COMPLIANCE

ASTM C 665, Type III, Class A, Category 1
ASTM E 96 Permeability; FSK – 0.05 Perms
ASTM E 84 Flame Spread 25 or less, Smoke Developed 50 or less

PERFORMANCE ADVANTAGES

- Formaldehyde-free – will not off-gas formaldehyde in the indoor environment.
- Fire-resistant and Noncombustible – (see Specification Compliance). FSK-25 faced insulation can be left exposed where codes permit.
- Moisture Control – the FSK-25 facing resists water vapor transmission.
- Light-reflective – when exposed, the FSK-25 reflective surface helps maximize lighting efficiency and may reduce lighting requirements.
- Thermal Efficiency – provides effective resistance to heat transfer with R-values up to R-30 (RSI-5.3).
- Sound Control – reduces transmission of sound through exterior walls and floor/ceiling assemblies.
- Noncorrosive – does not accelerate corrosion of pipes, wiring or metal studs.
- Durable – unaffected by moisture, oil, grease and most acids. It will not rot, mildew or otherwise deteriorate.
- Resilient – bonded glass fibers will not pull apart during normal applications and resist settling, breakdown and sagging from vibration.
- Flexible – forms readily around corners and curved surfaces.

FSK-25 Faced Batts

Flame-resistant Formaldehyde-free Thermal and Acoustical Fiber Glass Insulation

Visit our website at www.jm.com
Or call: 1-800-654-3103

BUILDING CODE COMPLIANCE AND FIRE HAZARD CLASSIFICATION

	ICBO	SBCCI	BOCA	IBC/IRC	Flame Spread*	Smoke Developed*
Unfaced	All Types	All Types	All Types	All Types/All Types	25	50

*Per ASTM E 84.

AVAILABLE FORMS*

Specification Compliance	R-value (hr-ft ² -°F/Btu)	RSI-value (m ² -°K/Watts)	Thickness**		Width***			
			(in)	(mm)	Metal Framing (in)	Wood Framing (in)	Metal Framing (mm)	Wood Framing (mm)
ASTM C 665	30	5.3	10 1/4	260	16, 24	16, 24	406, 610	406, 610
FSK-25 faced	19	3.3	6 1/2	159	16, 24	15, 23	406, 610	381, 584
Type III, Class A	13	2.3	3 1/4, 3 3/4	89, 92	16, 24	15	406, 610	381
	11	1.9	3 1/4, 3 3/4	89, 92	16, 24	15, 23	406, 610	381, 584

* Consult your local sales representative or product availability chart for other available sizes and R-values (RSI-values).

** Thickness may vary by producing location.

*** Product sizes may vary at plant locations; consult your local sales representative for other available sizes. Standard product lengths include 48, 93 and 96 inch batts.

SHORT FORM SPECIFICATION

All insulation shown on drawings or specified herein shall be "Johns Manville FSK-25 Faced Flame-resistant Formaldehyde-free Fiber Glass Insulation." Thermal resistance "R" (RSI) values of the insulation shall be R (RSI) _____ in ceilings, R (RSI) _____ in walls, and R (RSI) _____ in floors over unheated spaces. The product shall have an FHC rating of 25/50 or less.

LIMITATIONS OF USE

Check applicable building codes.



Properly insulating a structure using Johns Manville building insulation helps preserve our environment by reducing energy consumption for heating and cooling, reducing the pollution resulting from fuel burning, reducing the emission of hazardous air pollutants during manufacturing and reducing waste through the utilization of recycled materials. Look for the cross and globe emblem on Johns Manville building insulation which indicates independent certification by Scientific Certification Systems, Inc. of 25% or more recycled glass content.

Technical specifications as shown in this literature are intended to be used as general guidelines only. The physical and chemical properties of FSK-25 faced thermal and acoustical fiber glass insulation listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the sales office nearest you for current information. All Johns Manville products are sold subject to Johns Manville's Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville Limited Warranty and Limitation of Remedy or for information on other Johns Manville thermal and acoustical insulation and systems, call or write to the 800 number or address listed below.



Distributed by:

Building Insulation Division

717 17th Street (80202)
P.O. Box 5108
Denver, CO 80217-5108
1-800-654-3103
www.jm.com