

TECTUM ACOUSTICAL PERFORMANCE
SOUND ABSORPTION COEFFICIENTS

	125	250	500	1000	2000	4000	NRC	MOUNTING	TEST REPORT
TECTUM E ROOF DECK PANELS									
Thickness									
2" Tectum, 2" EPS	.19	.34	.71	1.00	.83	.93	.70	A	RAL - A91 - 212
2½" Tectum, 2" EPS	.28	.38	.82	.91	.90	.92	.75	A	RAL - A91 - 210
3" Tectum, 2" EPS	.22	.48	1.02	.79	.99	.97	.80	A	RAL - A91 - 206

Please click on the test number to view or download the actual test.