

TECTUM ACOUSTICAL PERFORMANCE

SOUND ABSORPTION COEFFICIENTS

	125	250	500	1000	2000	4000	NRC	MOUNTING	TEST REPORT
<b>INTERIOR PANELS</b>									
Panel Type									
1"	.06	.13	.24	.45	.82	.64	.40	A	A120037
1"	.07	.15	.36	.65	.71	.81	.45	D-20	RAL - A86 - 44
1"	.16	.43	1.00	1.05	.79	.98	.80	C-20	RAL - A86 - 49
1"	.32	.70	1.09	.93	.76	.94	.85	C-40	RAL - A86 - 50
1½"	.07	.22	.48	.82	.64	.96	.55	A	RAL - A86 - 42
1½"	.15	.26	.62	.83	.70	.91	.60	D-20	RAL - A86 - 45
1½"	.24	.57	1.17	.87	.93	.87	.90	C-20	RAL - A86 - 48
1½"	.40	.84	1.18	.84	.94	.88	.95	C-40	RAL - A86 - 51
2"	.15	.26	.62	.94	.62	.92	.60	A	RAL - A86 - 41
2"	.15	.36	.74	.82	.82	.92	.70	D-20	RAL - A86 - 46
2"	.24	.67	1.14	.87	1.06	.96	.95	C-20	RAL - A86 - 47
2"	.42	.89	1.19	.85	1.08	.94	1.00	C-40	RAL - A86 - 52

Please click on the test number to view or download the actual test.