



**TECTUM ACOUSTICAL PERFORMANCE
SOUND ABSORPTION COEFFICIENTS**

	125	250	500	1000	2000	4000	NRC	MOUNTING	TEST REPORT
TECTUM CEILING PANELS									
Panel Type									
1½" x 24" x 24" Lay-In	.44	.43	.33	.49	.66	.77	.50	E-400	A 75 - 89

Please click on the test number to view or download the actual test.