COVERAGE FOR 10.1 FL. OZ. CARTRIDGE (298 mL)

COVERAGE FOR 28 FL. OZ. CARTRIDGE (857 mL)

		Width							
		1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Depth	1/8"	99	49	33	24	20	16	14	12
	1/4"		24	20	12	10	8	7	6
	3/8"			11	8	6	5	5	4
	1/2"				6	5	4	3	3

Width 1/8" 1/4" 3/8" 1/2" 5/8" 3/4" 7/8" 1" Depth 1/8" 288 145 95 71 58 48 40 36 1/4" 71 36 29 23 17 58 20 3/8" 11 32 23 17 16 13 1/2" 17 14 11 10 8

LINEAR FEET PER 10.1 FL. OZ. CARTRIDGE

LINEAR FEET PER 28 FL, OZ, CARTRIDGE

COVERAGE FOR 20 FL. OZ. SAUSAGE (600 mL)

	Width								
		1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Depth	1/8"	192	97	63	48	39	31	27	12
	1/4"		48	39	24	19	15	14	6
	3/8"			21	15	11	10	9	4
	1/2"				11	10	8	7	3

LINEAR FEET PER 20 FL. OZ. SAUSAGE

1"

COVERAGE CHART FOR 1.5 GALLON PAIL (5.67 L)

Width 1/8" 1/4" 3/8" 5/8" 3/4" 7/8" 1/2"

Depth	1/8"	1848	924	615	462	369	308	264	231
	1/4"		412	308	231	185	153	132	116
	3/8"			204	153	123	102	87	77
	1/2"				116	92	77	66	57

COVERAGE CHART FOR 5 GALLON PAIL (18.9 L)

		Width							
_		1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Depth	1/8"	6153	3077	2048	1538	1228	1025	879	769
	1/4"		1372	1026	779	616	510	440	386
	3/8"			679	510	410	340	290	256
	1/2"				386	306	256	220	190

LINEAR FEET PER 1.5 GALLON PAIL

LINEAR FEET PER 5 GALLON PAIL

PRIMER COVERAGE RECOMMENDATIONS

For one quart of primer, coverage is as follows:

1 unit	5 gallon pail
5 units	1.5 gallon unit
7 gallons	1 gallon unit

NOTE: All values are approximations and can vary due to joint dimension variations, porosity, and texture of substrates. Yield per cartridge is approximate due to variables beyond Bostik's control such as irregular joint configuration

and installation technique.	TABLE 3:CHEM-CALK® 915ASTM C-794 ADHESION-IN-PEELTO COMMON CONSTRUCTION SURFACES*				
	Surface Mill Finished Aluminum** Anodized Aluminum Steel** Galvanized Steel Stainless Steel** Fiberglass ABS** Rigid PVC** Plywood*** Concrete*** Brick Granite Marble** Limestone*** * Values given above are not intended to be used in ** With primer, value is >25, Cohesive -100.	Failure Type – % Adhesive – 100 Cohesive – 100 Adhesive – 100 Adhesive – 100 Adhesive – 100 Adhesive – 100 Adhesive – 100 Cohesive – 100 Cohesive – 100 Cohesive – 100 Cohesive – 100 Cohesive – 100 Adhesive – 100 Specification preparation.			
	Peer values are reduced when unprimed samples	are water-immersed.			

C79