

DuPont™ Thru-Wall Flashing

PHYSICAL PROPERTIES DATA SHEET

Performance Testing

Total Thickness (mils)	ASTM D751	40
Membrane Thickness (mils)	ASTM D751	25
Butyl Adhesive Thickness (mils)	ASTM D751	15
Tensile Strength MD (lbs/in)*	ASTM D412	900
Tensile Strength CD (lbs/in)*	ASTM D412	700
Elongation % MD*	ASTM D412	200
Elongation % CD*	ASTM D412	270
Tear Strength MD (lbs/in)*	ASTM D624	55
Tear Strength CD (lbs/in)*	ASTM D624	70
Hydrohead (cm H ₂ O)*	AAT CC 127	800
Low Temperature Flexibility	ASTM D146	-25°F

*All values nominal.

For more information about DuPont™ Tyvek® Weather Barrier Systems, please call 1-800-44-Tyvek or visit us at www.Construction.Tyvek.com

CAUTION: DuPont™ Thru-Wall Flashing and its release paper are slippery; avoid walking on the product.

DuPont™ Thru-Wall Flashing is combustible and should be protected from flame and other high heat sources.



The miracles of science™

DuPont™

Thru-Wall Flashing